DIN EN 1965-2:2011-07 (E)

Structural adhesives - Corrosion - Part 2: Determination and classification of corrosion to a brass substrate

Contents

Page

Foreword 3

1 Scope 4

2 Normative references 4

3 Terms and definitions 4

4 Principle 4

5 Products, materials and apparatus 4
5.1 Solvent 4
5.2 Brass electrode, consisting of 0,1 mm thick brass, Ms63F45 or Ms63F55 of width 10 mm ... 4
5.3 Etching solution, consisting of 73 % concentrated sulfuric acid (98 %), 26 % concentrated nitric acid (63 %), 0,5 % sodium chloride, 0,5 % carbon black 4
5.4 Conditioning chamber, capable of maintaining a hot/humid climate in accordance with EN ISO 291 5
5.5 Direct current source, (100 ± 5) V, e.g. a battery, or rectifying equipment with a maximum permissable electrodyne alternating current not greater than 1 % 5
5.6 Magnifier, with a magnification of 2,5 × 5
5.7 Electrode and clamping, in accordance with Figure 1 5

6 Preparation of the brass substrate 7

7 Test specimens 7

8 Procedure 7

9 Discolouration/corrosion 8

10 Test report 8

Annex A (normative) Gradings for the appearance of plus pole and minus pole test foils at the surface of contact at the test specimen 9

Bibliography 10