

# ISO 34-2:2011-11 (E)

## Rubber, vulcanized or thermoplastic - Determination of tear strength - Part 2: Small (Delft) test pieces

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Principle .....</b>	<b>1</b>
<b>4</b>	<b>Apparatus .....</b>	<b>1</b>
<b>5</b>	<b>Calibration .....</b>	<b>2</b>
<b>6</b>	<b>Test pieces .....</b>	<b>2</b>
<b>6.1</b>	<b>Shape and dimensions .....</b>	<b>2</b>
<b>6.2</b>	<b>Measurement of dimensions .....</b>	<b>2</b>
<b>6.3</b>	<b>Time interval between vulcanization and testing .....</b>	<b>6</b>
<b>6.4</b>	<b>Number .....</b>	<b>6</b>
<b>7</b>	<b>Temperature of test .....</b>	<b>6</b>
<b>8</b>	<b>Procedure .....</b>	<b>6</b>
<b>9</b>	<b>Expression of results .....</b>	<b>6</b>
<b>10</b>	<b>Precision .....</b>	<b>7</b>
<b>11</b>	<b>Test report .....</b>	<b>7</b>
<b>Annex A (informative) Precision .....</b>		<b>8</b>
<b>Annex B (normative) Calibration schedule .....</b>		<b>12</b>
<b>Bibliography .....</b>		<b>13</b>