

# ISO 14627:2012-07 (E)

Fine ceramics (advanced ceramics, advanced technical ceramics) - Test method for fracture resistance of silicon nitride materials for rolling bearing balls at room temperature by indentation fracture (IF) method

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Normative references .....</b>	<b>1</b>
<b>3</b>	<b>Terms and definitions .....</b>	<b>1</b>
<b>4</b>	<b>Principle .....</b>	<b>2</b>
<b>5</b>	<b>Apparatus .....</b>	<b>2</b>
<b>5.1</b>	<b>Testing machine .....</b>	<b>2</b>
<b>5.2</b>	<b>Indenter .....</b>	<b>2</b>
<b>5.3</b>	<b>Verification by standard reference materials .....</b>	<b>3</b>
<b>6</b>	<b>Test specimens .....</b>	<b>3</b>
<b>6.1</b>	<b>General .....</b>	<b>3</b>
<b>6.2</b>	<b>Thickness .....</b>	<b>3</b>
<b>6.3</b>	<b>Surface finish .....</b>	<b>3</b>
<b>7</b>	<b>Procedure .....</b>	<b>3</b>
<b>7.1</b>	<b>Specimen placement .....</b>	<b>3</b>
<b>7.2</b>	<b>Specimen leveling .....</b>	<b>3</b>
<b>7.3</b>	<b>Clean the indenter .....</b>	<b>3</b>
<b>7.4</b>	<b>Application of test load .....</b>	<b>3</b>
<b>7.5</b>	<b>Acceptability of indentations .....</b>	<b>4</b>
<b>7.6</b>	<b>Number of indentations .....</b>	<b>4</b>
<b>7.7</b>	<b>Measurement of indentation size .....</b>	<b>5</b>
<b>7.8</b>	<b>Measurement of crack size .....</b>	<b>5</b>
<b>8</b>	<b>Calculation .....</b>	<b>5</b>
<b>9</b>	<b>Test report .....</b>	<b>6</b>
<b>Bibliography .....</b>		<b>8</b>