

# ISO 21483:2013-11 (E)

## Determination of solubility in nitric acid of plutonium in unirradiated mixed oxide fuel pellets (U,Pu)O<sub>2</sub> (Index)

---

<b>Contents</b>		<b>Page</b>
Foreword .....		iv
<b>1</b>	<b>Scope .....</b>	<b>1</b>
<b>2</b>	<b>Principle .....</b>	<b>1</b>
<b>3</b>	<b>Interferences .....</b>	<b>1</b>
<b>4</b>	<b>Reagents .....</b>	<b>1</b>
4.1	Concentrated nitric acid .....	1
4.2	Nitric acid high .....	1
4.3	Nitric acid low .....	1
4.4	Concentrated hydrofluoric acid .....	1
4.5	Mixture of acid .....	1
4.6	Sodium hydroxide .....	2
<b>5</b>	<b>Apparatus .....</b>	<b>2</b>
5.1	Analytical balance .....	2
5.2	Dissolution apparatus with total reflux condenser .....	2
5.3	Dissolution apparatus without total reflux condenser .....	2
5.4	Second dissolution apparatus (polytetrafluoroethylene, PTFE, high density polyethylene, HDPE) .....	2
5.5	Filter apparatus .....	2
<b>6</b>	<b>Sampling .....</b>	<b>2</b>
<b>7</b>	<b>Procedure .....</b>	<b>3</b>
7.1	Preparation of the sample .....	3
7.2	Dissolution procedure .....	3
7.3	Treatment of the residue .....	3
7.4	Plutonium determination .....	3
7.5	Repeat solubility test .....	3
<b>8</b>	<b>Expression of results .....</b>	<b>4</b>
8.1	Method of calculation .....	4
8.2	Total uncertainty of the Pu measurement .....	4
<b>9</b>	<b>Test report .....</b>	<b>4</b>
Bibliography .....		5