

ISO 18061:2014-06 (E)

Fine Ceramics (Advanced Ceramics, Advanced Technical Ceramics) - Determination of antiviral activity of semiconducting photocatalytic materials - Test method using bacteriophage Q-beta

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Symbols	2
5	Principle	3
6	Materials	3
6.1	Strains and preparation for tests	3
6.2	Media	5
7	Apparatus and equipment	6
7.1	Test equipment	6
7.2	Cover film	7
7.3	Moisture preservation glass plate	7
7.4	Glass tube or glass rod	7
7.5	Paper filter	7
7.6	Fluorescent ultraviolet lamp	8
7.7	UV radiometer	8
7.8	Punched metal sheet	8
7.9	Centrifuge	9
7.10	Sterilized syringe filter unit	9
8	Test piece	9
9	Procedure	10
9.1	General	10
9.2	Procedure for preparation of bacteria suspension	10
9.3	Procedure of preparation of test bacteriophage solution	10
9.4	Procedure of test for photocatalytic antiviral activity	11
9.5	UV irradiation condition	11
9.6	Measurement of titre of bacteriophage	12
10	Calculation	13
10.1	General	13
10.2	Calculate titre of bacteriophage	13
10.3	Test requirement fulfilment validation	13
10.4	Photocatalyst antiviral activity value calculation	14
10.5	Antiviral activity value calculation without photocatalyst	15
11	Test report	15

Annex A (informative) Referenced data of comparison between influenza virus and bacteriophage Q-beta	16
Annex B (informative) Comparison of photocatalytic activities determined using ATCC23631-B1 and NBRC20012	18