

ISO 6892-3:2015-04 (E)

Metallic materials - Tensile testing - Part 3: Method of test at low temperature

Contents		Page
Foreword		v
Introduction		vi
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Symbols and designations	2
5	Principle	3
6	Test piece	3
7	Determination of original cross-sectional area (S_0)	3
8	Marking the original gauge length (L_0)	3
9	Apparatus	3
9.1	Force measuring system	3
9.2	Extensometer	3
9.3	Cooling device	3
9.3.1	General	3
9.3.2	Permitted deviations of temperature	4
9.3.3	Measurement of temperature	4
9.3.4	Verification of the temperature-measuring system	5
10	Test conditions	5
10.1	Setting the force zero point	5
10.2	Gripping of the test piece, fixing of the extensometer and cooling of the test piece, not necessarily in the following sequence	5
10.2.1	Method of gripping	5
10.2.2	Fixing of the extensometer and establishing the gauge length	5
10.2.3	Cooling of the test piece	6
10.3	Testing rate based on strain rate control (Method A)	6
10.3.1	General	6
10.3.2	Strain rate for the determination of the upper yield strength (R_{eH}) or proof strength properties (R_p and, if required, R_t)	6
10.3.3	Strain rate for the determination of the lower yield strength (R_{eL}) and percentage yield point extension (A_e) if required	7
10.3.4	Strain rate for the determination of the tensile strength (R_m), percentage elongation after fracture (A), percentage reduction area (Z), and, if required, percentage total extension at the maximum force (A_{gt}), percentage plastic extension at maximum force (A_g)	7
10.4	Method of testing with expanded strain rate ranges (Method B)	7
10.4.1	General	7
10.4.2	Rate for the determination of yield strength or proof strength properties	7
10.4.3	Rate for the determination of tensile strength	8
10.5	Choice of the method and rates	8
10.6	Documentation of the chosen testing conditions	8

11	Determination or calculation of the properties	8
12	Test report	8
13	Measurement uncertainty	9
14	Figures	10
15	Annexes	11
	Annex B (informative) Example for cooling curves of steel depending on test piece dimensions and the specified test temperature in ethanol and liquid nitrogen	17
	Annex C (informative) Measurement uncertainty	21
	Bibliography	22