

ISO 28706-4:2016-01 (E)

Vitreous and porcelain enamels - Determination of resistance to chemical corrosion - Part 4: Determination of resistance to chemical corrosion by alkaline liquids using a cylindrical vessel

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Principle	1
4	Reagents	2
5	Apparatus and material	2
6	Test specimens	7
7	Procedure	7
8	Expression of results	8
8.1	Total loss in mass per unit area	8
8.2	Corrosion rate	8
9	Hot 0,1 mol/l sodium hydroxide test	9
9.1	General	9
9.2	Test solution, c(NaOH) = 0,1 mol/l	9
9.3	Test temperature	9
9.4	Duration of the test	9
9.5	Test report	9
10	Hot 1,0 mol/l sodium hydroxide test	10
10.1	General	10
10.2	Test solution, c(NaOH) = 1,0 mol/l	10
10.3	Test temperature	10
10.4	Duration of the test	10
10.5	Test report	10
11	Other test solutions	11
11.1	General	11
11.2	Test solution	11
11.3	Test temperature	11
11.4	Duration of the test	11
11.5	Test report	11
Bibliography		12