

DIN EN ISO 28706-4:2016-07 (E)

Vitreous and porcelain enamels - Determination of resistance to chemical corrosion - Part 4: Determination of resistance to chemical corrosion by alkaline liquids using a cylindrical vessel (ISO 28706-4:2016)

Contents		Page
European foreword		3
Foreword		4
Introduction		5
1 Scope		7
2 Normative references		7
3 Principle		7
4 Reagents		8
5 Apparatus and material		8
6 Test specimens		13
7 Procedure		13
8 Expression of results		14
8.1 Total loss in mass per unit area		14
8.2 Corrosion rate		14
9 Hot 0,1 mol/l sodium hydroxide test		15
9.1 General		15
9.2 Test solution, $c(\text{NaOH}) = 0,1 \text{ mol/l}$		15
9.3 Test temperature		15
9.4 Duration of the test		15
9.5 Test report		15
10 Hot 1,0 mol/l sodium hydroxide test		16
10.1 General		16
10.2 Test solution, $c(\text{NaOH}) = 1,0 \text{ mol/l}$		16
10.3 Test temperature		16
10.4 Duration of the test		16
10.5 Test report		16
11 Other test solutions		17
11.1 General		17
11.2 Test solution		17
11.3 Test temperature		17
11.4 Duration of the test		17
11.5 Test report		17
Bibliography		18