

ISO 19810:2017-04 (E)

Fine ceramics (advanced ceramics, advanced technical ceramics) - Test method for self-cleaning performance of semiconducting photocatalytic materials under indoor lighting environment - Measurement of water contact angle

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	3
5	Test apparatus	3
5.1	Instruments and apparatus	3
5.2	Reagents	4
5.3	Laboratory temperature and humidity	4
6	Test piece preparation	4
7	Test procedures	4
7.1	Measurement of water contact angle	4
7.2	Test piece pretreatment	5
7.3	Visible light irradiation and measurement of contact angle after n h of visible light irradiation, 4(n)	6
8	Calculation of test results	8
8.1	Guide to the rounding of numbers	8
8.2	Calculation of contact angle	8
8.3	Conditions for a valid test	9
8.4	Initial contact angle halving time, $n_{1/2}$	9
8.5	Contact angle reduction time, n_{10°	10
9	Reporting of test results	10
10	Test measurement examples	11
Bibliography		12