

DIN EN ISO 6892-2:2018-09 (E)

Metallic materials - Tensile testing - Part 2: Method of test at elevated temperature (ISO 6892-2:2018)

Contents	Page
European foreword	3
Foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Symbols and designations	7
5 Principle	8
6 Test piece	8
7 Determination of original cross-sectional area (S_0)	8
8 Marking the original gauge length (L_0)	8
9 Apparatus	8
10 Test conditions	10
10.1 Setting the force zero point	10
10.2 Gripping of the test piece, fixing of the extensometer and heating of the test piece, not necessarily in the following sequence	10
10.2.1 Method of gripping	10
10.2.2 Fixing of the extensometer and establishing the gauge length	10
10.2.3 Heating of the test piece	11
10.3 Testing rate based on strain rate control (Method A)	11
10.3.1 General	11
10.3.2 Strain rate for the determination of the upper yield strength (R_{eH}) or proof strength properties (R_p and, if required, R_t)	11
10.3.3 Strain rate for the determination of the lower yield strength (R_{eL}) and percentage yield point extension (A_e), if required	11
10.3.4 Strain rate for the determination of the tensile strength (R_m), percentage elongation after fracture (A), percentage reduction area (Z), and, if required, percentage total extension at the maximum force (A_{gt}), percentage plastic extension at maximum force (A_g)	12
10.4 Method of testing with expanded strain rate ranges (Method B)	12
10.4.1 General	12
10.4.2 Rate for the determination of yield strength or proof strength properties	12
10.4.3 Rate for the determination of tensile strength	12
10.5 Choice of the method and rates	12
10.6 Documentation of the chosen testing conditions	13
11 Determination or calculation of the properties	13
12 Test report	13
13 Measurement uncertainty	14
14 Figures	14
15 Annexes	15
Annex A (informative) Addition to ISO 6892-1:2016, Annexes B and D	17
Annex B (informative) Measurement uncertainty	23
Bibliography	26