ISO 48-2:2018 (E)

Rubber, vulcanized or thermoplastic — Determination of hardness — Part 2: Hardness between 10 IRHD and 100 IRHD

Contents

Foreword

Introduction

1 Scope

2 Normative references

3 Terms and definitions

4 Principle

5 Apparatus

5.1 General
5.2 Methods N, H, L and M
5.3 Methods CN, CH, CL and CM
5.3.1 Cylindrical surfaces of radius greater than 50 mm
5.3.2 Surfaces with double curvature of large radius greater than 50 mm
5.3.3 Cylindrical surfaces of radius 4 mm to 50 mm or small test pieces with double curvature
5.3.4 Small O-rings and articles of radius of curvature less than 4 mm

6 Test pieces

6.1 General
6.2 Methods N, H, L and M
6.2.1 General
6.2.2 Thickness
6.2.2.1 Methods N and H
6.2.2.2 Method L
6.2.2.3 Method M
6.2.3 Lateral dimensions
6.2.3.1 Methods N, H and L
6.2.3.2 Method M
6.3 Methods CN, CH, CL and CM

7 Time interval between forming and testing

8 Conditioning of test pieces

9 Temperature of test

10 Procedure

11 Number of readings

12 Expression of results

13 Precision

14 Test report

Annex A (informative) Empirical relationship between indentation and hardness

Annex B (informative) Precision results from interlaboratory test programmes

B.1 General
B.2 Precision results from the ITPs carried out between 1985 and 1989
B.2.1 Programme details
B.2.2 Precision results (1985 to 1989)
B.3 Precision results from the ITP carried out in 2004
B.3.1 Programme details
B.3.2 Precision results (2004)
B.4 Precision results from the ITP carried out in 2007
B.4.1 Programme details
B.4.2 Precision results (2007)
B.5 Guidance for using precision results

Page count: 23