

DIN 50928:2019-03 (E)

Corrosion of metals - Testing and assessment of the corrosion protection of coated metallic materials under corrosive action by aqueous media

Contents		Page
Foreword		4
Introduction		5
1	Scope	6
2	Normative references	6
3	Terms and definitions	7
4	Coatings	9
4.1	Thin coatings	9
4.2	Thick coatings	9
5	Electrochemical corrosion protection	9
6	Corrosive environments	9
7	Types of corrosive action	10
7.1	General	10
7.2	Cathodic effects	10
7.3	Anodic effects	10
7.4	Physico-chemical action	10
8	Appearance and causes of changes in coatings and of substrate corrosion	11
8.1	Reduction in the adhesive strength of an undamaged and pinhole-free coating	11
8.2	Pitting of the substrate in the region of pinholes or other defects in the coating	11
8.3	Cathodic disbonding	11
8.4	Blistering	11
8.4.1	General	11
8.4.2	Cathodic blisters	11
8.4.3	Anodic blisters	12
8.4.4	Neutral blisters	12
9	Methods of testing the properties of coatings	12
9.1	Adhesive strength	12
9.2	Specific layer resistance of coating	12
9.3	Cathodic disbonding	13
9.4	Electrochemical blistering	14
9.5	Blistering due to a gradient in temperature	15
9.6	Cathodic effect of coated surfaces	15
9.6.1	General	15
9.6.2	Measurement of cell current	15
9.6.3	Measurement of polarization current	16
10	Importance of coating properties for the effectiveness of corrosion protection	17
10.1	Adhesive strength	17
10.2	Cathodic disbonding	17
10.3	Blistering	17
11	Assessment of the effectiveness of corrosion protection and minimum requirements	17

11.1	Durability and duration of the test	17
11.2	Specific layer resistance of coating	18
11.3	Applications and requirements for coatings	18
11.3.1	General	18
11.3.2	Corrosion protection of convex surfaces	18
11.3.3	Corrosion protection of planar surfaces	19
11.3.4	Corrosion protection of concave surfaces	19
11.4	Cell formation and pitting	19
Bibliography		20
Figures Figure 1 -- Coplanar element for the measurement of the cell current		16