

ISO 643:2019-12 (E)

Steels - Micrographic determination of the apparent grain size

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
3.1	Grains	1
3.2	General	2
4	Symbols	2
5	Principle	3
6	Selection and preparation of the specimen	4
6.1	Test location	4
6.2	Revealing ferritic grain boundaries	5
6.3	Revealing austenitic and prior-austenitic grain boundaries	5
6.3.1	General	5
6.3.2	"Bechet-Beaujard" method by etching with aqueous saturated picric acid solution	5
6.3.3	"Kohn" method by controlled oxidation	6
6.3.4	"McQuaid-Ehn" method by carburization at 925 °C	7
6.3.5	Proeutectoid ferrite method	8
6.3.6	Bainite or gradient-quench method	9
6.3.7	Sensitization of austenitic stainless and manganese steels	9
6.3.8	Other methods for revealing prior-austenitic grain boundaries	9
7	Characterization of grain size	10
7.1	Characterization by an index	10
7.1.1	Formulae	10
7.1.2	Assessment by comparison with standard grain size charts	10
7.1.3	Planimetric method	11
7.1.4	Estimation of the index	11
7.2	Characterization by the intercept method	11
7.2.1	Linear intercept segment method	11
7.2.2	Circular intercept segment method	12
7.2.3	Assessment of results	13
8	Test report	14
Annex A (informative) Summary of methods for revealing ferritic, austenitic or prior-austenitic grain boundaries in steels		15
Annex B (normative) Evaluation method		16
Bibliography		21