

DIN ISO 48-2:2021-02 (E)

Rubber, vulcanized or thermoplastic - Determination of hardness - Part 2: Hardness between 10 IRHD and 100 IRHD (ISO 48-2:2018)

Contents		Page
Foreword		5
Introduction		6
1	Scope	7
2	Normative references	8
3	Terms and definitions	8
4	Principle	9
5	Apparatus	9
5.1	General	9
5.2	Methods N, H, L and M	9
5.3	Methods CN, CH, CL and CM	11
5.3.1	Cylindrical surfaces of radius greater than 50 mm	11
5.3.2	Surfaces with double curvature of large radius greater than 50 mm	11
5.3.3	Cylindrical surfaces of radius 4 mm to 50 mm or small test pieces with double curvature	11
5.3.4	Small O-rings and articles of radius of curvature less than 4 mm	11
6	Test pieces	11
6.1	General	11
6.2	Methods N, H, L and M	11
6.2.1	General	11
6.2.2	Thickness	11
6.2.3	Lateral dimensions	12
6.3	Methods CN, CH, CL and CM	12
7	Time interval between forming and testing	13
8	Conditioning of test pieces	13
9	Temperature of test	13
10	Procedure	13
11	Number of readings	13
12	Expression of results	14
13	Precision	14
14	Test report	16
Annex A (informative) Empirical relationship between indentation and hardness		18
Annex B (informative) Precision results from interlaboratory test programmes		21
Bibliography		29