

# ISO/TS 21236-2:2021 (E)

## Nanotechnologies — Clay nanomaterials — Part 2: Specification of characteristics and measurements for clay nanoplates used for gas-barrier film applications

---

### Contents

	Foreword
	Introduction
1	Scope
2	Normative references
3	Terms and definitions
4	Abbreviated terms
5	Characteristics and measurement methods
5.1	General
5.2	Mineral composition
5.3	Chemical composition
5.4	Cation exchange capacity
5.5	Particle size
5.6	Loss on ignition
5.7	Methylene blue adsorption capacity
5.8	Aspect ratio
5.9	Film formability
5.10	Viscosity
6	Reporting
Annex A	(informative) Measurement protocols
A.1	General
A.2	Mineral composition
A.3	Chemical composition
A.4	Cation exchange capacity
A.4.1	pH 7 - 1 N ammonium acetate solution. 2 N Ammonia water and 2 N acetic acid are mixed in equal amounts and prepared with concentrated ammonia water or glacial acetic acid to give a pH of 7. The pH is measured using a glass electrode pH meter.
A.4.2	pH 7-80 % ethyl alcohol. 20 volumes of purified water and 80 volumes of ethyl alcohol are mixed and prepared with a sodium hydroxide solution to give a pH of 7 while being examined with a BTB test paper.
A.4.3	10 % potassium chloride solution. Dissolve 100 g of potassium chloride in 900 ml of purified water.
A.5	Particle size
A.5.1	General
A.5.2	Measurement protocol
A.5.3	Suspension liquid
A.6	Loss on ignition
A.7	Methylene blue adsorption capacity
A.8	Aspect ratio
A.9	Film formability
A.9.1	General
A.9.2	Film formability
A.9.3	Flexibility test
A.10	Viscosity

**Annex B (informative) Principles of a gas barrier using clay nanoplates**

**B.1 General**

**B.2 Basic approach**

**B.3 Gas barrier film preparation**

**B.4 Relationship between clay nanoplate characteristics and high gas-barrier film properties**

**Annex C (informative) Value chains of clay nanoplate materials**

**Annex D (informative) Example of reporting sheet**

**Page count: 18**