

ISO 18219-2:2021 (E)

Leather — Determination of chlorinated hydrocarbons in leather — Part 2: Chromatographic method for middle-chain chlorinated paraffins (MCCPs)

Contents

	Foreword
	Introduction
1	Scope
2	Normative references
3	Terms and definitions
4	Principle
5	Apparatus and materials
6	Reagents
7	Sampling
8	Sample preparation and analysis
8.1	Preparation of MCCPs calibration solution (50 µg/ml) with 55 % chlorination degree
8.2	Extraction of leather
8.3	Sulfuric acid clean-up
8.4	GC-ECNI-MS Determination
9	Expression of results
9.1	Evaluation
9.2	Ions used for quantification
9.3	Interference to MCCPs determination
9.4	Calculation
9.5	Precision
10	Test report
Annex A	(informative) Gas chromatographic (GC-ECNI-MS) analysis operating parameters
A.1	Suggested GC-ECNI-MS conditions
A.2	GC-ECNI-MS system optimization
A.3	Calibration and calculation
Annex B	(informative) Liquid chromatographic (LC-MS/MS) analysis operating parameters
B.1	Introduction
B.2	Apparatus and materials
B.3	Reagents
B.4	Preparation of MCCPs calibration solution (50 µg/ml) with 55 % Cl
B.5	Extraction of leather and preparation of analytical solution
B.6	Instrumental parameters
B.7	Calculation
Annex C	(informative) Integration with peak shape evaluation (PSE) with GC-ECNI-MS
C.1	Introduction
C.2	Dilution
C.3	Peak shape evaluation (PSE)
C.4	Quantifier/qualifier ratio
C.5	Interference

C.6 Interpretation of Figures C.1 to C.4

Page count: 15