

ISO/TS 12025:2021 (E)

Nanomaterials — Quantification of nano-object release from powders by generation of aerosols

Contents

	Foreword
	Introduction
1	Scope
2	Normative references
3	Terms and definitions
3.1	General terms
3.2	Terms related to particle properties and measurement
4	Symbols
5	Factors influencing results of nano-object release from powders
5.1	Test generation method selection
5.2	Material properties influencing nano-object release from powder
5.3	Test stages
6	Test requirements
6.1	General
6.2	Safety assessment
6.3	Sample preparation
6.4	Sample treatment
6.4.1	Dustiness generation methods
6.4.1.1	Selection of methods
6.4.1.2	Reference test methods
6.4.1.3	Dynamic method
6.4.2	Dispersing methods for aerosol generation
6.4.3	Sample treatment execution and report
6.5	Measurement of aerosolized nano-objects
6.5.1	Selection of the measuring method
6.5.2	Transport and sampling parameters
6.5.3	Considerations before testing
6.5.4	Size and concentration measurement results
6.5.4.1	Nano-object number release
6.5.4.2	Specific nano-object number release
6.5.4.3	Size range limits
6.5.4.3.1	General
6.5.4.3.2	Lower size limit
6.5.4.3.3	Upper size limit
6.5.5	Particle size distribution and other characteristic measurement parameters
7	Requirements for test setups and protocols
8	Test report
Annex A	(informative) Considerations for the selection of the sample treatment procedure
A.1	Dustiness reference test methods
A.2	Dispersing methods
Annex B	(informative) Dustiness reference test methods

Annex C (informative) Dynamic method

- C.1 Principle**
- C.2 Equipment**
- C.3 Procedure**
- C.4 Discussion**

Annex D (informative) Dispersing methods

Annex E (informative) Selection of the nano-object measuring method

- E.1 Methods and performance parameters of actual aerosol measurement devices**
- E.2 Influence of instrument measuring principle on equivalent diameter**

Annex F (informative) Dry dispersion intensity in measuring devices

Page count: 32