

DIN EN ISO 17636-1:2022-10 (E)

Non-destructive testing of welds - Radiographic testing - Part 1: X- and gamma-ray techniques with film (ISO 17636-1:2022)

Contents		Page
European foreword		4
Foreword		5
1	Scope	7
2	Normative references	7
3	Terms and definitions	8
4	Symbols and abbreviated terms	9
5	Classification of radiographic techniques	10
6	General preparations and requirements	10
6.1	Protection against ionizing radiation	10
6.2	Surface preparation and stage of manufacture	10
6.3	Location of the weld in the radiograph	11
6.4	Identification of radiographs	11
6.5	Marking	11
6.6	Overlap of films	11
6.7	Types and positions of image quality indicators (IQIs)	11
6.8	Evaluation of image quality	12
6.9	Minimum image quality values	12
6.10	Personnel qualification	13
7	Recommended techniques	13
7.1	Test arrangements	13
7.1.1	General	13
7.1.2	Single-wall penetration of plane objects (see Figure 1)	14
7.1.3	Single-wall penetration of curved objects with the source outside the object (see Figures 2 to 4)	14
7.1.4	Single-wall penetration of curved objects with the source inside the object for panoramic exposure (see Figures 5 to 7)	15
7.1.5	Single-wall penetration of curved objects with the source located off-centre and inside the object (see Figures 8 to 10)	16
7.1.6	Double-wall penetration and double-image evaluation (DWDI) of pipes with the elliptic technique and the source and the film outside the object (see Figure 11)	17
7.1.7	Double-wall penetration and double-image evaluation (DWDI) with the perpendicular technique and source and film outside the object (see Figure 12)	17
7.1.8	Double-wall penetration and single-image evaluation (DWSI) of curved objects for evaluation of the wall next to the film (see Figures 13 to 16)	17
7.1.9	Penetration of objects with different material thicknesses (see Figure 17 to 19)	19
7.2	Choice of tube voltage and radiation source	19
7.2.1	X-ray devices up to 1 000 kV	19
7.2.2	Other radiation sources	20
7.3	Film systems and metal screens	21
7.4	Alignment of beam	23
7.5	Reduction of scattered radiation	23
7.5.1	Metal filters and collimators	23
7.5.2	Interception of backscattered radiation	23

7.6	Source-to-object distance.....	24
7.7	Maximum area for a single exposure.....	26
7.8	Optical density of radiograph.....	26
7.9	Processing.....	27
7.10	Film viewing conditions.....	27
8	Test report.....	27
Annex A	(normative) Number of exposures for acceptable testing of a circumferential butt weld.....	29
Annex B	(normative) Minimum image quality values.....	34
Annex C	(informative) Calculation of maximum X-ray tube voltages from Figure 20.....	41
Bibliography	42