

# DIN 50159-1:2022-06 (E)

## Metallic materials - Hardness testing with the UCI method - Part 1: Test method

<b>Contents</b>		<b>Page</b>
Foreword .....		2
Introduction .....		4
1 Scope .....		5
2 Normative references .....		5
3 Terms and definitions .....		5
4 Principle .....		5
5 Symbols .....		6
6 Indication of hardness according to the UCI method .....		6
7 Designation .....		6
8 Test device .....		6
9 Specimen .....		9
9.1 Shape .....		9
9.2 Thickness and mass .....		9
9.3 Surface preparation .....		10
9.4 Hardness testing on metallic coatings .....		11
9.5 Adjustment .....		11
10 Procedure .....		11
11 Measurement uncertainty of results .....		12
12 Test report .....		12
Annex A (normative) Periodic checking of the testing device by the user .....		14
Annex B (informative) Measurement uncertainty of the measured hardness values .....		15
B.1 General .....		15
B.2 Uncertainty of measurement for hardness testing .....		16
B.2.1 Procedure without error (method 1) .....		16
B.2.2 Representation of the measurement result .....		16
B.2.3 Procedure using the measurement uncertainty of the hardness testing device (method 2) .....		19
Bibliography .....		21
Figures Figure 1 -- Example of the indication of hardness according to the UIC method .....		6
Figure 2 -- Schematic set-up of a UCI probe .....		7
Figure 3 -- Example adjustment curves for the determination of the HV (UCI) hardness from the frequency shift .....		8

<b>Figure B.1 -- Structure of the metrological chain for the definition and transfer of hardness scales .</b>	<b>15</b>
<b>Tables Table 1 -- Symbols, their designations and units .....</b>	<b>6</b>
<b>Table 2 -- Typical applications of the UCI method .....</b>	<b>9</b>
<b>Table 3 -- Maximum permissible surface roughness Ra .....</b>	<b>10</b>
<b>Table 4 -- Relationship of surface roughness to grinding medium grain size for steels .....</b>	<b>10</b>
<b>Table A.1 -- Limit deviations .....</b>	<b>14</b>
<b>Table B.1 -- Determination of the expanded uncertainty using method M1 .....</b>	<b>17</b>
<b>Table B.2 -- Determination of the inhomogeneity of the specimen .....</b>	<b>19</b>