

DIN 50905-3:2022-09 (E)

Corrosion of metals - Corrosion testing - Part 3: Values of corrosion with non-uniform and localized corrosion attack without mechanical stresses

Contents

Page

Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions.....	5
4 Measurands and their determination	5
4.1 General	5
4.2 Surface area exposed to corrosion	6
4.3 Test specimen thickness prior to corrosion test.....	6
4.4 Change in mass.....	7
4.5 Density	7
4.6 Exposure time.....	7
4.7 Attack depth.....	7
4.7.1 Attack depth in the case of shallow pitting	7
4.7.2 Attack depth in the case of pitting	8
4.7.3 Attack depth in the case of selective corrosion	8
4.8 Number of localized corrosion attacks	9
4.9 Area of localized corrosion attacks	9
5 Corrosion characteristics and their calculation.....	9
5.1 Corrosion characteristics in the case of shallow pitting.....	9
5.1.1 General	9
5.1.2 Average reduction in thickness	10
5.1.3 Maximum attack depth.....	10
5.1.4 Maximum penetration rate.....	10
5.1.5 Depth factor	10
5.2 Corrosion characteristics in the case of pitting.....	11
5.2.1 General	11
5.2.2 Maximum attack depth.....	11
5.2.3 Maximum penetration rate.....	11
5.2.4 Pit density.....	11
5.2.5 Proportional area of localized corrosion attack	12
5.3 Corrosion characteristics in the case of selective corrosion.....	12
5.3.1 General	12
5.3.2 Maximum attack depth.....	12
5.3.3 Maximum penetration rate.....	12
Bibliography.....	13

Figures

Figure 1 — Determining the attack depth with exposure to corrosion on one side only.....	7
Figure 2 — Determining the attack depth with exposure to corrosion on both sides.....	8
Figure 3 — Determining the attack depth in the case of selective corrosion, taking intergranular corrosion as example	9

Tables

Table 1 — Measurands, symbols and units	6
Table 2 — Measurands for calculating corrosion characteristics as a function of the corrosion mechanism.....	6
Table 3 — Corrosion characteristics in the case of shallow pitting.....	9
Table 4 — Corrosion characteristics in the case of pitting	11
Table 5 — Corrosion characteristics in the case of selective corrosion.....	12