

DIN EN ISO 16539:2022-08 (E)

Corrosion of metals and alloys - Accelerated cyclic corrosion tests with exposure to synthetic ocean water salt-deposition process - „Dry” and „wet” conditions at constant absolute humidity (ISO 16539:2013)

Contents

	Page
European foreword	3
Foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Test solution	7
3.1 Preparation of the mixed salt solution	7
3.2 pH adjustment	7
3.3 Preparation of the test solution	7
4 Apparatus	8
4.1 Component protection	8
4.2 Exposure cabinet	8
4.3 Salt deposition device	8
4.4 Temperature and humidity control device	8
4.5 Rinse treatment of specimens	8
4.6 Types of apparatus	8
5 Test specimens	9
6 Salt deposition measurement method	9
7 Arrangement of the test specimens	9
8 Operating conditions and procedure	9
9 Treatment of specimens after test	14
10 Continuity of tests	14
11 Duration of tests	14
12 Evaluation of results	14
13 Test report	14
Annex A (informative) Combined cyclic test instrument with salt deposition unit (two cabinets)	16
Annex B (informative) Combined cyclic test instrument with salt deposition unit (one cabinet)	17
Annex C (informative) Salt deposition method by manual spraying	18
Annex D (informative) Recommended periods of testing	20
Annex E (informative) Methods for evaluation of corrosivity of test	22
Bibliography	24