

# ISO 9813:2023-10 (E)

## Corrosion of metals and alloys - Performance test method for corrosion inhibitors used in chemical cleaning of industry equipment

---

Contents	Page
Foreword.....	iv
Introduction.....	v
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Apparatus.....</b>	<b>2</b>
4.1 Container used in the static test below 100 °C.....	2
4.2 Container used in the static test above 100 °C.....	2
4.3 Dynamic test device.....	2
4.4 Specimen suspending device.....	3
4.5 Constant temperature device.....	3
4.6 Oven.....	3
4.7 Analytical balance.....	4
4.8 Vernier caliper.....	4
4.9 Magnifier.....	4
4.10 Colorimetric tube.....	4
4.11 Pipette.....	4
<b>5 Reagents and materials.....</b>	<b>4</b>
5.1 Experimental water.....	4
5.2 Acetone.....	4
5.3 Ethanol.....	4
5.4 Abrasive paper.....	4
<b>6 Test specimens.....</b>	<b>4</b>
<b>7 Pretreatment of specimens.....</b>	<b>4</b>
<b>8 Test condition.....</b>	<b>5</b>
8.1 Ratio of solution volume to surface area of immersed metal.....	5
8.2 Concentration of cleaning agent.....	5
8.3 Concentration of corrosion inhibitor.....	5
8.4 Temperature.....	5
8.5 Test duration.....	5
8.6 Other provisions.....	5
<b>9 Procedure.....</b>	<b>5</b>
9.1 Static test.....	5
9.2 Dynamic test.....	6
9.3 Calculation of the corrosion rate.....	7
9.4 Intergranular corrosion and stress corrosion.....	7
9.5 Solubility and dispersion test.....	7
9.6 Time effectiveness test.....	8
<b>10 Report.....</b>	<b>8</b>
<b>Annex A (informative) Result of corrosion inhibitor test.....</b>	<b>9</b>
<b>Bibliography.....</b>	<b>12</b>