

ISO 6507-1:2023-10 (E)

Metallic materials - Vickers hardness test - Part 1: Test method

Contents		Page
	Foreword	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	Symbols and designations	2
4.1	Symbols and designations used in this document.....	2
4.2	Designation of hardness number.....	3
5	Principle	3
6	Testing machine	4
6.1	Testing machine.....	4
6.2	Indenter.....	4
6.3	Diagonal measuring system.....	4
7	Test piece	5
7.1	Test surface.....	5
7.2	Preparation.....	5
7.3	Thickness.....	5
7.4	Tests on curved surfaces.....	5
7.5	Support of unstable test pieces.....	5
7.6	Metallic and other inorganic coatings.....	5
8	Procedure	6
8.1	Test temperature.....	6
8.2	Test force.....	6
8.3	Periodic verification.....	6
8.4	Test piece support and orientation.....	6
8.5	Focus on test surface.....	7
8.6	Test force application.....	7
8.7	Prevention of the effect of shock or vibration.....	7
8.8	Minimum distance between adjacent indentations.....	7
8.9	Measurement of the diagonal length.....	8
8.10	Calculation of hardness value.....	8
9	Uncertainty of the results	8
10	Test report	9
	Annex A (normative) Minimum thickness of the test piece in relation to the test force and hardness	10
	Annex B (normative) Tables of correction factors for use in tests made on curved surfaces	12
	Annex C (normative) Procedure for periodic checking of the testing machine, diagonal measuring system and indenter by the user	16
	Annex D (informative) Uncertainty of the measured hardness values	18
	Annex E (informative) Vickers hardness measurement traceability	25
	Annex F (informative) CCM — Working group on hardness	29
	Annex G (informative) Adjustment of Köhler illumination systems	30
	Annex H (normative) Determining the Vickers hardness of metallic and other inorganic coatings	31
	Bibliography	35