

ISO 7249:2024-02 (E)

Textiles - Fibres - Determination of burning behaviour by oxygen index

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	2
5	Apparatus	2
6	Preparation of the test specimens	5
6.1	Test specimens for staple fibres	5
6.2	Test specimens for filament yarns	6
6.3	Marking of test specimens	6
7	Preconditioning and conditioning	6
7.1	Atmosphere for conditioning	6
7.2	Pre-conditioning	6
7.3	Conditioning	6
7.4	Test specimens storage	6
8	Procedure for determination of oxygen index (OI)	7
8.1	Test environment	7
8.2	Initial volume fraction of oxygen	7
8.3	Test specimen mounting	7
8.4	Gas control unit adjustment	7
8.5	Test specimen ignition	7
8.6	Burning behaviour observation and recording	8
8.7	Volume fractions of oxygen successive selection	8
8.8	Preliminary volume fraction of oxygen determination	8
8.9	Volume fraction of oxygen changes	9
9	Calculation and expression of results	9
9.1	Calculation of oxygen index (OI)	9
9.2	Determination of K	9
9.3	Verification of step size of oxygen volume fraction changes	10
9.4	Example of test results	11
9.5	Precision	11
10	Test report	11
Annex A (informative)	Example of simple spinning	12
Annex B (informative)	Typical example of test results	14
Annex C (informative)	Precision experiments	16
Bibliography		17