

ISO 13680:2020-05 (E)

Petroleum and natural gas industries - Corrosion-resistant alloy seamless tubular products for use as casing, tubing, coupling stock and accessory material - Technical delivery conditions

Contents	Page
Foreword	vii
Introduction	viii
1 Scope	1
2 Normative references	2
3 Terms, definitions, abbreviated terms and symbols	4
3.1 Terms and definitions.....	4
3.2 Abbreviated terms.....	6
3.3 Symbols.....	7
4 General	8
4.1 Dual normative references.....	8
4.2 Units of measurement.....	8
5 Information supplied by the purchaser	8
6 Manufacturing process	11
6.1 Melting practices.....	11
6.2 Product manufacturing process.....	11
6.3 Pipe end sizing.....	11
6.4 Straightening.....	11
6.5 Process requiring validation.....	12
6.6 Traceability.....	12
6.7 Manufacturing procedure qualification test.....	12
6.8 Process for update of alloys and/or grades.....	12
7 Material requirements	13
7.1 Chemical composition.....	13
7.2 Tensile properties.....	13
7.3 Hardness properties.....	13
7.4 Charpy V-notch test properties — General requirements.....	13
7.4.1 Evaluation of test results.....	13
7.4.2 Critical thickness.....	14
7.4.3 Specimen size, orientation and hierarchy.....	14
7.4.4 Alternative size impact test specimens.....	14
7.4.5 Sub-size test specimens.....	14
7.4.6 Test temperature.....	14
7.5 Charpy V-notch — Absorbed energy requirements for coupling stock and accessory material — All grades.....	14
7.5.1 General.....	14
7.5.2 Requirements for all grades.....	15
7.6 Charpy V-notch — Absorbed energy requirements for pipe — All grades.....	15
7.7 Flattening requirements.....	16
7.8 Charpy V-notch test properties at low temperature for group 2.....	17
7.8.1 General.....	17
7.8.2 Evaluation of test results.....	17
7.8.3 Selection of test specimens.....	17
7.8.4 Test temperature.....	17
7.8.5 Absorbed energy requirements.....	17
7.9 Corrosion properties.....	17
7.9.1 General.....	17
7.9.2 Pitting corrosion properties for group 2.....	18

7.10	Microstructure properties	18
	7.10.1 Group 1	18
	7.10.2 Group 2	18
	7.10.3 Groups 3 and 4	18
7.11	Surface condition	18
7.12	Defects	19
	7.12.1 Pipe	19
	7.12.2 Coupling stock and accessory material	19
	7.12.3 Process control plan	19
8	Dimensions, masses and tolerances	19
8.1	Outside diameter, wall thickness and mass	19
8.2	Length	20
8.3	Tolerances	20
	8.3.1 Tolerance on outside diameter, wall thickness and mass	20
	8.3.2 Inside diameter, <i>d</i>	20
	8.3.3 Straightness	20
	8.3.4 Drift requirements	20
8.4	Product ends	20
9	Inspection and testing	21
9.1	Test equipment	21
9.2	Type and frequency of tests	21
9.3	Testing of chemical composition	21
	9.3.1 Chemical analysis	21
	9.3.2 Test method	21
	9.3.3 Chromium depletion test — Groups 2, 3 and 4	21
9.4	Testing of mechanical characteristics	22
	9.4.1 Test lot	22
	9.4.2 Selection and preparation of samples and test pieces	22
9.5	Tensile test	22
	9.5.1 Orientation and size of test pieces	22
	9.5.2 Test method	22
	9.5.3 Invalidation of test	22
	9.5.4 Retest	22
9.6	Hardness test	23
	9.6.1 Test pieces	23
	9.6.2 Test method	23
	9.6.3 Invalidation of tests	24
	9.6.4 Periodic checks of hardness-testing machines	24
	9.6.5 Verification of hardness-testing machines and indenters	24
	9.6.6 Retests	25
9.7	Impact or flattening test	26
	9.7.1 Test pieces	26
	9.7.2 Frequency of testing	26
	9.7.3 Impact test method	26
	9.7.4 Flattening test method	27
	9.7.5 Impact test retest	27
	9.7.6 Flattening test retest	27
	9.7.7 Invalidation of tests	28
9.8	Impact test at low temperature for group 2	28
9.9	Pitting corrosion test for group 2	28
9.10	Microstructural examination	29
	9.10.1 Test pieces	29
	9.10.2 Test method	29
	9.10.3 Retest	30
9.11	Dimensional testing	30
	9.11.1 General	30
	9.11.2 Outside diameter	30
	9.11.3 Wall thickness at end of products	30
	9.11.4 Wall thickness of product body	30
9.12	Drift test	31
	9.12.1 Non-upset and external upset pipe	31
	9.12.2 Internal upset pipe	31

9.12.3	Drift mandrel coating.....	31
9.13	Length.....	31
9.14	Straightness.....	31
9.15	Mass determination.....	31
9.16	Visual inspection.....	31
9.16.1	General.....	31
9.16.2	Pipe body, coupling stock and accessory material.....	32
9.16.3	Pipe ends.....	32
9.16.4	Disposition.....	32
9.17	Non-destructive examination.....	32
9.17.1	General.....	32
9.17.2	NDE personnel.....	33
9.17.3	Products.....	33
9.17.4	Pup joints.....	33
9.17.5	Untested ends.....	33
9.17.6	Upset ends.....	33
9.17.7	Reference standards.....	34
9.17.8	NDE system capability records.....	34
9.17.9	All product group 1.....	35
9.17.10	Full-body NDE of product — Groups 2, 3 and 4.....	35
9.17.11	Pipe, coupling stock and accessory material requiring further evaluation.....	35
9.17.12	Evaluation of indications (prove-up).....	35
9.17.13	Disposition of pipe containing defects.....	36
9.17.14	Disposition of coupling stock and accessory material containing defects.....	37
9.18	Positive material identification.....	37
10	Surface treatment.....	38
10.1	Group 1.....	38
10.2	Groups 2, 3 and 4.....	38
11	Marking.....	39
11.1	General.....	39
11.2	Colour-code identification.....	39
11.3	Marking content and sequence.....	39
11.4	Marking informative for couplings, pup joints and accessories after threading.....	40
12	Surface protection — Group 1.....	40
13	Documents.....	41
13.1	Electronic media.....	41
13.2	Retention of records.....	41
13.3	Test certificates.....	41
14	Handling, packaging and storage.....	42
14.1	General.....	42
14.2	Handling.....	42
14.3	Packaging.....	42
14.3.1	General.....	42
14.3.2	Identification.....	42
14.4	Storage.....	43
	Annex A (normative) Tables in SI units.....	44
	Annex B (normative) Figures in SI (USC) units.....	68
	Annex C (normative) Tables in USC units.....	73
	Annex D (normative) Purchaser inspection.....	97
	Annex E (normative) Cleanliness requirements.....	98
	Annex F (normative) Coupling blanks and accessory material from bar.....	100
	Annex G (normative) Product specification level 2 (PSL-2).....	115
	Annex H (normative) Standardized manufacturing procedure qualification test.....	117
	Annex I (informative) Photographic examples of microstructures, groups 2, 3 and 4.....	121
	Bibliography.....	125