

ISO 13680:2024-05 (E)

Oil and gas industries including lower carbon energy - Corrosion-resistant alloy seamless products for use as casing, tubing, coupling stock and accessory material - Technical delivery conditions

Contents		Page
Foreword		vi
1	Scope	1
2	Normative references	1
3	Terms, definitions, abbreviated terms and symbols	4
3.1	Terms and definitions	4
3.2	Abbreviated terms	6
3.3	Symbols	7
4	General	8
4.1	Dual normative references	8
4.2	Units of measurement	8
5	Information supplied by the purchaser	8
6	Manufacturing process	10
6.1	Melting practices	10
6.2	Product manufacturing process	10
6.3	Pipe end sizing	11
6.4	Straightening	11
6.5	Processes requiring validation	11
6.6	Traceability	12
6.7	Manufacturing procedure qualification test	12
6.8	Process for update of alloys and/or grades	12
7	Material requirements	12
7.1	Chemical composition	12
7.2	Tensile properties	13
7.3	Hardness properties	13
7.4	Charpy V-notch test properties -- General requirements	13
7.4.1	Evaluation of test results	13
7.4.2	Critical thickness	13
7.4.3	Specimen size, orientation and hierarchy	13
7.4.4	Alternative size impact test specimens	14
7.4.5	Sub-size test specimens	14
7.4.6	Test temperature	14
7.5	Charpy V-notch -- Absorbed energy requirements for coupling stock and accessory material -- All grades	14
7.5.1	General	14
7.5.2	Requirements for all grades	14
7.6	Charpy V-notch -- Absorbed energy requirements for pipe -- All grades	15
7.7	Flattening requirements	16
7.8	Charpy V-notch test properties at low temperature for group 2	16
7.8.1	General	16
7.8.2	Evaluation of test results	16
7.8.3	Selection of test specimens	17
7.8.4	Test temperature	17

7.8.5	Absorbed energy requirements	17
7.9	Corrosion properties	17
7.9.1	General	17
7.9.2	Pitting corrosion properties for group 2	17
7.10	Microstructure properties	17
7.10.1	Group 1	17
7.10.2	Group 2	17
7.10.3	Groups 3 and 4	18
7.11	Surface condition	18
7.12	Defects	18
7.12.1	Pipe	18
7.12.2	Coupling stock and accessory material	19
7.12.3	Process control plan	19
8	Dimensions, masses and tolerances	19
8.1	Outside diameter, wall thickness and mass	19
8.2	Length	19
8.3	Tolerances	19
8.3.1	Tolerance on outside diameter, wall thickness and mass	19
8.3.2	Inside diameter, d	20
8.3.3	Straightness	20
8.3.4	Drift requirements	20
8.4	Product ends	20
9	Inspection and testing	20
9.1	Test equipment	20
9.2	Type and frequency of tests	20
9.3	Testing of chemical composition	20
9.3.1	Chemical analysis	20
9.3.2	Test method	21
9.3.3	Chromium depletion test -- Groups 2, 3 and 4	21
9.4	Testing of mechanical characteristics	21
9.4.1	Test lot	21
9.4.2	Selection and preparation of samples and test pieces	21
9.5	Tensile test	21
9.5.1	Orientation and size of test pieces	21
9.5.2	Test method	21
9.5.3	Invalidation of test	22
9.5.4	Retest	22
9.6	Hardness test	22
9.6.1	Test pieces	22
9.6.2	Test method	22
9.6.3	Invalidation of tests	23
9.6.4	Periodic checks of hardness-testing machines	23
9.6.5	Verification of hardness-testing machines and indenters	24
9.6.6	Retests	25
9.7	Impact or flattening test	25
9.7.1	Test pieces	25
9.7.2	Frequency of testing	25
9.7.3	Impact test method	26
9.7.4	Flattening test method	26
9.7.5	Impact test retest	26
9.7.6	Flattening test retest	27
9.7.7	Invalidation of tests	27
9.8	Impact test at low temperature for group 2	27
9.9	Pitting corrosion test for group 2	27
9.10	Microstructural examination	28
9.10.1	Test pieces	28
9.10.2	Test method	28
9.10.3	Retest	29
9.11	Dimensional testing	29

9.11.1	General	29
9.11.2	Outside diameter	29
9.11.3	Wall thickness at end of products	29
9.11.4	Wall thickness of product body	30
9.12	Drift test	30
9.12.1	Non-upset and external upset pipe	30
9.12.2	Internal upset pipe	30
9.12.3	Drift mandrel coating	30
9.13	Length	30
9.14	Straightness	30
9.15	Mass determination	30
9.16	Visual inspection	30
9.16.1	General	30
9.16.2	Pipe body, coupling stock and accessory material	31
9.16.3	Pipe ends	31
9.16.4	Disposition	31
9.17	Non-destructive examination	31
9.17.1	General	31
9.17.2	NDE personnel	32
9.17.3	Products	32
9.17.4	Pup joints	32
9.17.5	Untested ends	32
9.17.6	Upset ends	33
9.17.7	Reference standards	33
9.17.8	NDE system capability records	33
9.17.9	All product group 1	34
9.17.10	Full-body NDE of product -- Groups 2, 3 and 4	34
9.17.11	Pipe, coupling stock and accessory material requiring further evaluation	34
9.17.12	Evaluation of indications (prove-up)	35
9.17.13	Disposition of pipe containing defects	35
9.17.14	Disposition of coupling stock and accessory material containing defects	36
9.18	Positive material identification	37
10	Surface treatment	37
10.1	Group 1	37
10.2	Groups 2, 3 and 4	37
11	Marking	38
11.1	General	38
11.2	Colour-code identification	38
11.3	Marking content and sequence	38
11.4	Marking for couplings, pup joints and accessories after threading	39
12	Surface protection -- Group 1	39
13	Documents	40
13.1	Electronic media	40
13.2	Retention of records	40
13.3	Test certificates	40
14	Handling, packaging and storage	41
14.1	General	41
14.2	Handling	41
14.3	Packaging	41
14.3.1	General	41
14.3.2	Identification	41
14.4	Storage	42
Annex A (normative) Tables in SI units		43
Annex B (normative) Figures in SI (USC) units		66

Annex C (normative) Tables in USC units	71
Annex D (normative) Purchaser inspection	94
Annex E (normative) Cleanliness requirements	95
Annex F (normative) Coupling blanks and accessory material from bar	97
Annex G (normative) Productspecificationlevel2(PSL-2)	111
Annex H (normative)Standardizedmanufacturingprocedurequalificationtest	113
Annex I (informative) Photographic examples of microstructures, groups 2, 3 and 4	117
Bibliography	121