

ISO 5351:2010-02 (E)

Pulps - Determination of limiting viscosity number in cupri-ethylenediamine (CED) solution

Contents		Page
Foreword		iv
Introduction		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Principle	2
5	Reagents and materials	3
6	Apparatus and materials	3
7	Calibration of viscometers	5
8	Sampling and preparation of sample	6
9	Procedure	6
9.1	Choice of mass concentration of solution	6
9.2	Weighing of test portion	7
9.3	Preparation of test solution	7
9.4	Determination of efflux time	7
10	Calculation	7
10.1	Viscosity ratio	7
10.2	Limiting viscosity number	8
10.3	Expression of results	8
11	Precision	8
11.1	General check using reference pulp	8
11.2	Repeatability	8
11.3	Reproducibility	9
12	Test report	9
Annex A (normative) Preparation and analysis of the cupri-ethylenediamine (CED) solution		10
Annex B (normative) Values of η_{sp}/c corresponding to different values of the viscosity ratio ratio (η_{sp}/c_0)		15
Annex C (informative) Calculation of degree of polymerization		18
Bibliography		19