

ISO 3549:2024-02 (E)

Zinc dust pigments for paints - Specifications and test methods

Contents		Page
Foreword		v
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Required characteristics and tolerances	1
5	Sampling	3
6	Determination of residue on sieve	3
6.1	Principle	3
6.2	Apparatus	3
6.3	Checking and cleaning the sieve	5
6.4	Procedure	5
6.5	Expression of results	5
7	Determination of total zinc content	6
7.1	Principle	6
7.2	Reagents	6
7.3	Procedure	7
7.3.1	Test portion	7
7.3.2	Determination	7
7.4	Expression of results	7
8	Determination of metallic zinc content	8
8.1	Principle	8
8.2	Reagents and materials	8
8.3	Procedure	9
8.3.1	General	9
8.3.2	Test portion	9
8.3.3	Determination	9
8.4	Expression of results	9
9	Determination of lead, cadmium and iron content	10
9.1	Principle	10
9.2	Reagents and materials	10
9.3	Apparatus	11
9.4	Procedure	11
9.4.1	Test portion	11
9.4.2	Preparation of test solutions	11
9.4.3	Determination	12
9.5	Expression of results	12
10	Determination of arsenic content	13
10.1	Principle	13
10.2	Reagents and materials	13
10.3	Apparatus	14
10.4	Procedure	15
10.4.1	Preparation of the calibration graph	15

10.4.2	Test portion	15
10.4.3	Preparation of the test solution	16
10.4.4	Determination	16
10.5	Expression of results	18
11	Determination of chloride content	18
11.1	Principle	18
11.2	Reagents and materials	18
11.3	Apparatus	18
11.4	Procedure	19
11.4.1	Preparation of the calibration graph	19
11.4.2	Determination	19
12	Determination of matter insoluble in acid	19
12.1	Reagents and materials	19
12.2	Apparatus	19
12.3	Procedure	19
12.3.1	Test portion	19
12.3.2	Determination	20
12.4	Expression of results	20
13	Test report	20
	Bibliography	21