

ISO 10893-10:2011-04 (E)

Non-destructive testing of steel tubes - Part 10: Automated full peripheral ultrasonic testing of seamless and welded (except submerged arc-welded) steel tubes for the detection of longitudinal and/or transverse imperfections

Contents		Page
Foreword		iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	2
4	General requirements	3
5	Test method	3
6	Reference tube	4
6.1	General	4
6.2	Types of reference notches	4
6.3	Dimensions of reference notches	5
7	Equipment calibration and checking	6
7.1	General	6
7.2	Adjustment of trigger/alarm level	6
7.3	Calibration check and recalibration	7
8	Acceptance	7
9	Test report	8
Annex A (normative) Testing on longitudinal imperfections of tubes with a ratio of the specified outside diameter to the average of the specified thickness range less than 5		9
Annex B (normative) Manual/semi-automated testing of untested ends and suspect areas		11