

ISO/TR 16043:2015-10 (E)

Iron ores - Determination of chlorine content - X-ray fluorescence spectrometric method

Contents		Page
Foreword		v
Introduction		vi
1	Scope	1
2	Principle	1
3	Reagents and materials	1
4	Apparatus	2
5	Sampling and samples	3
5.1	Laboratory sample	3
5.2	Preparation of test sample	3
5.2.1	Preparation of pre-dried test samples	3
5.2.2	Ores having significant contents of combined water or oxidizable compounds	4
6	Procedure	4
6.1	Preparation of discs	4
6.1.1	General	4
6.1.2	Weighing	4
6.1.3	Mixing	5
6.1.4	Fusion	5
6.1.5	Casting	5
6.1.6	Calibration discs	5
6.1.7	Test discs	6
6.1.8	Visual inspection	6
6.1.9	Disc storage	6
6.1.10	Cleaning of platinum ware	6
6.2	Measurements	7
6.2.1	General	7
6.2.2	Analytical lines	7
6.2.3	XRF generator settings	7
6.2.4	Crystals	7
6.2.5	Counting times	7
6.2.6	Collimators	8
6.2.7	Simultaneous-type instruments	8
6.2.8	Sample holders	8
6.2.9	Subsequent determinations	8
7	Calculation of results	8
7.1	General	8
7.2	Correction for background	9
7.3	Calibration	9
8	General treatment of results	10
8.1	Acceptability of background equivalent concentration (BEC)	10
8.2	Repeatability and permissible tolerances	10
8.3	Determination of analytical result	11
8.3.1	Mean of duplicates	11

8.3.2	Between-laboratories precision	11
8.4	Check for trueness	11
8.5	Calculation of final result	12
8.6	Oxide factor	12
9	Test report	12
Annex A (informative) Preparation of flux A		13
Annex B (informative) Preparation of flux B		15
Annex C (informative) Flowsheet of the procedure for the acceptance of analytical values for test samples		16
Annex D (informative) Derivation of repeatability and permissible tolerance		17
Bibliography		18