

DIN EN ISO 4829-1:2018-08 (E)

Steel and cast iron - Determination of total silicon contents - Reduced molybdsilicate spectrophotometric method - Part 1: Silicon contents between 0,05 % and 1,0 % (ISO 4829-1:2018)

Contents	Page
European foreword	3
Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Reagents	5
6 Apparatus	7
7 Sampling	8
8 Procedure	8
8.1 Test portion.....	8
8.2 Blank test.....	8
8.3 Determination.....	8
8.3.1 Dissolution of the test portion.....	8
8.3.2 Treatment of insoluble residue.....	9
8.3.3 Preparation of the test solution.....	9
8.3.4 Development of the colour.....	9
8.3.5 Spectrophotometric measurements.....	10
8.4 Establishment of the calibration curve.....	10
8.4.1 Preparation of the calibration solutions.....	10
8.4.2 Spectrophotometric measurements.....	10
8.4.3 Plotting of the calibration curves.....	10
9 Expression of results	11
9.1 Method of calculation.....	11
9.2 Precision.....	12
10 Test report	12
Annex A (informative) Additional information on the international interlaboratory test	13
Annex B (informative) Graphical representation of precision data	14
Bibliography	15