

# ISO 13956:2010-10 (E)

## Plastics pipes and fittings - Decohesion test of polyethylene (PE) saddle fusion joints - Evaluation of ductility of fusion joint interface by tear test

---

<b>Contents</b>		<b>Page</b>
<b>Foreword</b> .....		<b>iv</b>
<b>1</b>	<b>Scope</b> .....	<b>1</b>
<b>2</b>	<b>Normative references</b> .....	<b>1</b>
<b>3</b>	<b>Principle</b> .....	<b>1</b>
<b>4</b>	<b>Apparatus</b> .....	<b>1</b>
4.1	General .....	1
4.2	Tensile test equipment -- Type A1 or A2 .....	1
4.3	Compressive equipment -- Type B .....	3
4.4	Equipment -- Type C .....	3
<b>5</b>	<b>Sampling</b> .....	<b>4</b>
5.1	Preparation of test pieces .....	4
5.2	Number of test pieces .....	5
<b>6</b>	<b>Conditioning</b> .....	<b>5</b>
<b>7</b>	<b>Procedure</b> .....	<b>5</b>
<b>8</b>	<b>Test report</b> .....	<b>7</b>
<b>Annex A (informative) Recommended condition</b> .....		<b>9</b>
<b>Bibliography</b> .....		<b>10</b>