

DIN EN ISO 10580:2012-04 (E)

Resilient, textile and laminate floor coverings - Test method for volatile organic compound (VOC) emissions (ISO 10580:2010)

Contents		Page
Foreword		3
Introduction		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	6
4	Symbols and abbreviated terms	8
5	Apparatus	8
6	Sampling the product and transport and storage of sample	8
6.1	Sampling	8
6.2	Sample packaging and transport	9
6.3	Sample description	9
6.4	Storage of the sample prior to starting the testing	10
7	Preparation of test specimens	10
7.1	Specimens from rolls	10
7.2	Samples of rigid products such as tiles and planks	10
8	Emission test chamber system	11
8.1	General	11
8.2	Emission test chamber description	11
8.3	Air supply and mixing facilities	11
8.4	Airtightness	11
8.5	Air sampling manifold	11
8.6	Recovery and sink effects	12
9	Test conditions	12
9.1	Temperature and relative air humidity	12
9.2	Temperature and relative-air-humidity control systems	12
9.3	Supply-air quality and background concentration	13
9.4	Air velocity	13
9.5	Loading factor and air change rate	13
9.6	Air change rate in the emission test chamber	13
9.7	Emission test chamber airtightness	13
9.8	Efficiency of the internal emission-test-chamber air mixing	13
10	Preparation of emission test chamber	14
11	Test procedure	14
11.1	Test conditions in the emission test chamber	14
11.2	Background concentrations	14
11.3	Test specimen location in the emission test chamber	14
11.4	Time for measurements of test-chamber air concentration	14
11.5	Air sampling	14

12	Analysis of the air samples	16
12.1	Analysis of VOC	16
12.2	Analysis of formaldehyde and carbonyl compounds	16
13	Calculation of vapour concentrations and area-specific emission rates	16
14	Performance characteristics	16
15	Test report	17
	Annex A (informative) General description of an emission test chamber	18
	Annex B (informative) Evaluation systems	19
	Bibliography	24