

DIN EN ISO 11357-1:2023-06 (E)

Plastics - Differential scanning calorimetry (DSC) - Part 1: General principles (ISO 11357-1:2023)

Contents		Page
European foreword		4
Foreword		5
Introduction		6
1	Scope	7
2	Normative references	7
3	Terms and definitions	7
4	Basic principles	14
4.1	General	14
4.2	Heat-flux DSC	14
4.3	Power-compensation DSC	14
5	Apparatus and materials	15
6	Specimen	16
7	Test conditions and specimen conditioning	17
7.1	Test conditions	17
7.2	Conditioning of specimens	17
8	Calibration	17
8.1	General	17
8.2	Calibration materials	18
8.3	Temperature calibration	18
8.3.1	General	18
8.3.2	Procedure	18
8.3.3	Accuracy of calibration	19
8.4	Heat calibration	19
8.4.1	General	19
8.4.2	Procedure	20
8.4.3	Accuracy of calibration	20
8.5	Heat flow rate calibration	20
8.5.1	General	20
8.5.2	Procedure	21
9	Procedure	23
9.1	Setting up the apparatus	23
9.1.1	Switching on	23
9.1.2	Purge gas	23
9.1.3	Experimental conditions	23
9.1.4	Baseline determination	23
9.2	Loading the specimen into the crucible	23
9.2.1	General	23
9.2.2	Selection of crucibles	23
9.2.3	Weighing the specimen crucible	24
9.2.4	Loading the specimen	24
9.2.5	Determination of the mass of the specimen	24
9.3	Insertion of crucibles into the instrument	24
9.4	Performing measurements	24

9.4.1	General	24
9.4.2	Scanning mode	24
9.4.3	Isothermal mode	25
9.5	Post-run checks	26
9.5.1	Check for loss in mass	26
9.5.2	Inspection of specimens	26
9.5.3	Checking of crucibles and crucible holder	26
10	Test report	26
Annex A	(normative) Extended, high-precision, temperature calibration ^[12]	28
Annex B	(normative) Extended, high-precision, heat calibration	30
Annex C	(informative) Recommended calibration materials	32
Annex D	(informative) Interaction of calibration materials with different crucible materials	36
Annex E	(informative) General recommendations	38
Bibliography	40