

DIN 67510-1:2020-05 (E)

Phosphorescent pigments and products - Part 1: Measurement and marking at the producer

Contents

Page

Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Measurement.....	6
4.1 Measured objects	6
4.1.1 General	6
4.1.2 Phosphorescent pigments	6
4.1.3 Phosphorescent products.....	7
4.2 Requirements on the excitation apparatus	7
4.3 Excitation and measurement.....	8
4.3.1 Temperature.....	8
4.3.2 Illuminance measuring instrument	8
4.3.3 Procedure	8
4.4 Measurement of light decay	8
4.4.1 Luminance	8
4.4.2 Effect of stray light	10
4.4.3 Documentation of measured values.....	10
4.5 Determination of the decay time.....	10
4.6 Measurement record.....	10
5 Marking of phosphorescent properties	11
Annex A (informative) Mathematical method for the approximate determination of the decay time	12
A.1 Application	12
A.2 Procedure	12
A.3 Example of linear extrapolation.....	12
A.4 Example of parabolic extrapolation.....	14
Annex B (normative) Determination of the complete and relative saturating excitation	16
B.1 Complete saturating excitation	16
B.2 Relative saturating excitation	16
Annex C (normative) Classification by the manufacturer	17
Annex D (informative) Classification by the manufacturer for applications outside safety marking	18
Annex E (informative) Comparison of luminance under various excitation conditions	19
Bibliography	22

Figures

Figure A.1 — Linear fit	14
Figure A.2 — Parabolic fit	15

Tables

Table A.1 — Extract from the measurement record.....	13
Table A.2 — Calculation	13
Table A.3 — Extract from the measurement record.....	14
Table A.4 — Calculation	15
Table C.1 — Classification by the manufacturer	17
Table D.1 — Classification by the manufacturer for applications outside safety marking.....	18
Table E.1 — Influence of the excitation duration in min or h on the luminances at different colour temperatures in Kelvin (K) with different light sources at an illuminance of 25 lx	20
Table E.2 — Influence of the excitation duration in min or h on the luminances at different colour temperatures in Kelvin (K) with different light sources at an illuminance of 50 lx	21