

DIN EN 1977:2013-04 (E)

Copper and copper alloys - Copper drawing stock (wire rod)

Contents		Page
Foreword		3
Introduction		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Designations	5
4.1	Material	5
4.2	Product	6
5	Ordering information	7
6	Requirements	7
6.1	Composition	7
6.2	Elongation	7
6.3	Electrical properties	7
6.4	Annealability	12
6.5	Hydrogen embrittlement	12
6.6	Scale adhesion	13
6.7	Dimensions and tolerances	13
6.8	Surface condition	13
6.9	Joins	13
7	Sampling	13
7.1	General	13
7.2	Analysis (oxygen only) and measurement of diameter of Cu-ETP1 (CW003A) drawing stock	14
7.3	Annealability testing of Cu-ETP1 (CW003A) drawing stock	14
7.4	Analysis (other than oxygen) and measurement of elongation and electrical properties of Cu-ETP1 (CW003A) drawing stock	14
7.5	Tests on drawing stock in grades other than Cu-ETP1 (CW003A)	14
8	Test methods	15
8.1	Analysis	15
8.2	Elongation	15
8.3	Electrical resistivity	15
8.4	Annealability	16
8.5	Hydrogen embrittlement	16
8.6	Scale adhesion	16
8.7	Rounding of results	16
9	Declaration of conformity and inspection documentation	16
9.1	Declaration of conformity	16
9.2	Inspection documentation	17
10	Marking	17
Annex A (informative)	Information on electrical resistivity and conductivity relationships	18

A.1	Volume resistivity	18
A.2	Standard annealed copper (IACS)	18
A.3	Commercial annealed copper	18
A.4	Nominal mass resistivity	18
A.5	Differences between measured and nominal values	19
Annex B (normative)	Rapid Elongation Test method (AR-Test) for diameter 8 mm Cu-ETP1 wire rod	20
B.1	General	20
B.2	Procedure	20
B.3	Test results	22
Bibliography		23