DIN EN 15703-2:2015-03 (E)

Copper and copper alloys - Determination of manganese content - Part 2: Flame atomic absorption spectrometric method (FAAS)

Contents

Page

Foreword 3

1 Scope 4

2 Normative references 4

3 Principle 4

4 Reagents 4
4.1 Hydrochloric acid, HCl (= 1,19 g/ml) 4
4.2 Nitric acid, HNO3 (= 1,40 g/ml) 4
4.3 Hydrofluoric acid, HF (= 1,13 g/ml) 4
4.4 Nitric acid solution, 1 + 1 4
4.5 Lanthanum(III) chloride solution, 100 g/l 4
4.6 Sulphuric acid, H2SO4 (= 1,84 g/ml) 4
4.7 Sulphuric acid solution, 1 + 9 5
4.8 Manganese stock solution, 1,0 g/l Mn 5
4.9 Manganese standard solution, 0,10 g/l 5
4.10 Manganese standard solution, 0,010 g/l 5
4.11 Copper matrix solution, 20 g/l Cu 5
4.12 Copper matrix solution, 2 g/l Cu 5

5 Apparatus 5
5.1 Atomic absorption spectrometer, fitted with an air/acetylene burner 5
5.2 Manganese hollow-cathode lamp 6

6 Sampling 6

7 Procedure 6
7.1 Preparation of the test portion solution 6
7.2 Blank test 7
7.3 Check test 7
7.4 Establishment of the calibration curve 7
7.5 Determination 10

8 Expression of results 10
8.1 Use of the calibration curve 10
8.2 Use of the bracketing method 11

9 Precision 12

10 Test report 13

Bibliography 14