ISO 15661:2020 (E)

Copper and nickel sulfide ores and concentrates — Determination of total chlorine content — Alkaline fusion and potentiometric titration method

Contents

Foreword

1 Scope

2 Normative references

3 Terms and definitions

4 Principle

5 Reagents

6 Apparatus

7 Instrument operating parameters

8 Sample

8.1 Laboratory sample
8.2 Test sample

9 Procedure

9.1 Number of blank testing
9.2 Number of determinations
9.3 Determination
9.3.1 General
9.3.2 Decomposition of the test portion by fusion with a mixture of carbonate salts
9.3.2.1 Decomposition
9.3.2.2 Dissolution of the test sample
9.3.3 Decomposition of the test portion by fusion with a mixture of potassium salts
9.3.3.1 Decomposition
9.3.3.2 Dissolution of the test sample
9.3.4 Oxidation of sulfide
9.3.5 Preparation of solution for titration
9.3.6 Potentiometric titration
9.3.6.1 Titration of blank tests
9.3.6.2 Titration of samples

10 Expression of results

11 Precision and accuracy

11.1 Expression of precision
11.2 Method for obtaining the final result
11.3 Precision between laboratories
11.4 Check of trueness

12 Test report

Annex A (informative) Procedure for the preparation and determination of the mass of a predried test portion

A.1 Scope
A.2 Principle
A.3 Reagents
A.4 Apparatus

A.5 Procedure
A.5.1 Preparation of the weighing vessel
A.5.2 Test portion
A.5.3 Determination of the test portion dry mass
A.6 Calculation of the dry mass of the test portion

Annex B (normative) Flow chart of the procedure for the acceptance of analytical values for test samples

Page count: 15