

ISO 18768-2:2022-06 (E)

Organic coatings on aluminium and its alloys - Methods for specifying decorative and protective organic coatings on aluminium - Part 2: Liquid coatings

Contents	Page
Foreword	vi
Introduction	vii
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Information to be supplied by the customer to the surface processor	3
5 Metal preparation and pretreatment	5
5.1 Material (substrate).....	5
5.2 Pretreatment of the substrate.....	5
5.2.1 General.....	5
5.2.2 Degreasing etching and rinsing.....	5
5.2.3 Anodic oxidation coating.....	5
5.2.4 Chemical conversion coatings.....	5
5.2.5 Alternative pretreatment.....	6
6 Categories	6
7 Tests	8
7.1 General.....	8
7.2 Appearance.....	8
7.2.1 General.....	8
7.2.2 Measurement.....	8
7.2.3 Requirement.....	8
7.3 Colour.....	9
7.3.1 General.....	9
7.3.2 Visual method.....	9
7.3.3 Instrumental method.....	9
7.4 Gloss.....	9
7.4.1 Measurement.....	9
7.4.2 Requirement.....	10
7.5 Brightness (distinctness of image).....	10
7.5.1 General.....	10
7.5.2 Measurement.....	10
7.5.3 Requirement.....	10
7.6 Thickness.....	10
7.6.1 General.....	10
7.6.2 Measurement.....	11
7.6.3 Requirement.....	11
7.7 Hardness (pencil).....	11
7.7.1 Measurement.....	11
7.7.2 Requirement.....	11
7.8 Adhesion.....	11
7.8.1 General.....	11
7.8.2 Scratch circular roll method.....	12
7.8.3 Dry adhesion test.....	12
7.8.4 Wet adhesion test.....	13
7.8.5 Pull-off test.....	13
7.9 Impact resistance.....	13

7.9.1	General	13
7.9.2	Measurement	14
7.9.3	Requirement	14
7.10	Multi-impact stone chipping resistance	14
7.10.1	General	14
7.10.2	Measurement	14
7.10.3	Requirement	14
7.11	Abrasion resistance	14
7.11.1	General	14
7.11.2	Falling sand test	14
7.11.3	Rotating, abrasive rubber-wheel test	15
7.11.4	Friction coefficient	15
7.12	Cupping test	15
7.12.1	Measurement	15
7.12.2	Requirement	15
7.13	Flexibility	16
7.13.1	General	16
7.13.2	T-bend test	16
7.13.3	Cylindrical mandrel bend test	17
7.14	Processing resistance	17
7.14.1	Measurement	17
7.14.2	Requirement	17
7.15	Permeating depths of ink	17
7.15.1	Measurement	17
7.15.2	Requirement	17
7.16	Chemical resistance	18
7.16.1	General	18
7.16.2	Acid resistance	18
7.16.3	Alkali resistance	19
7.16.4	Detergent resistance	20
7.16.5	Mortar resistance	20
7.16.6	Contamination resistance	21
7.16.7	Oil resistance	22
7.17	Solvent resistance	22
7.17.1	General	22
7.17.2	Measurement	22
7.17.3	Requirement	22
7.18	Corrosion resistance	22
7.18.1	General	22
7.18.2	Neutral salt spray (NSS) test	23
7.18.3	Acetic acid salt spray (AASS) test	23
7.18.4	Copper-accelerated acetic acid salt spray (CASS) test	24
7.18.5	Cyclic corrosion test	24
7.18.6	Filiform corrosion resistance test	25
7.18.7	Resistance to humid atmosphere containing sulfur dioxide	25
7.19	Humidity resistance	25
7.19.1	Condensation resistance	25
7.19.2	High temperature and high RH test	26
7.19.3	Wet heat resistance test	26
7.19.4	Thermocycling resistance test	26
7.20	Water resistance	27
7.20.1	Water immersion method	27
7.20.2	Autoclave test	27
7.20.3	Boiling water resistance	27
7.21	Temperature resistance	28
7.21.1	Dry heat resistance test	28
7.21.2	Roasting resistance test	28
7.21.3	Low-temperature resistance test	28
7.22	Surface tension	29
7.22.1	General	29
7.22.2	Measurement	29
7.22.3	Requirement	29
7.23	Hydrophilicity	29
7.23.1	General	29

7.23.2	Measurement.....	29
7.23.3	Requirement.....	30
7.24	Thermal viscosity.....	30
7.24.1	General.....	30
7.24.2	Measurement.....	30
7.24.3	Requirement.....	31
7.25	Resistivity.....	31
7.25.1	General.....	31
7.25.2	Measurement.....	31
7.25.3	Requirement.....	31
7.26	Weathering resistance.....	31
7.26.1	General.....	31
7.26.2	Outdoor exposure.....	31
7.26.3	Accelerated weathering resistance.....	32
7.27	Sealing compounds adhesion.....	32
7.27.1	Measurement.....	32
7.27.2	Requirement.....	33
Annex A (informative) Summary of information to be supplied by the customer to the surface processor.....		34
Annex B (informative) Coating materials.....		37
Annex C (informative) Categories for architectural application.....		38
Bibliography.....		39