

ISO 2107:2023-09 (E)

Aluminium and aluminium alloys - Wrought products - Temper designations

Contents		Page
	Foreword	iv
1	Scope	1
2	Normative references	1
3	Terms and definitions	1
4	Basic temper designations	2
4.1	F — as fabricated.....	2
4.2	O — annealed.....	3
4.3	H — strain-hardened.....	3
4.4	W — solution heat-treated.....	3
4.5	T — precipitation hardened to produce stable tempers other than F, O or H.....	3
5	Subdivisions of O temper designations	3
5.1	O1 — high-temperature annealed to accentuate ultrasonic response and provide dimensional stability.....	3
5.2	O3 — homogenized.....	3
6	Subdivisions of H temper designations	4
6.1	General.....	4
6.2	First digit after H.....	4
6.3	Second digit after H.....	4
6.4	Third digit after H.....	5
6.5	Other digits after H.....	6
7	Subdivisions of T temper designations	6
7.1	First digits (numerals 1 to 10) after T.....	6
7.2	Additional digits added to designations T1 to T10.....	8
7.3	Assigned additional digits for stress-relieved T tempers.....	8
7.3.1	Stress-relieved by stretching.....	8
7.3.2	Stress relieved by compressing.....	9
7.3.3	Stress relieved by combined stretching and compressing.....	9
7.4	Assigned additional digits for stress-relieved W tempers.....	9
7.5	Assigned additional digits for variations of T7 type tempers.....	9
7.6	Assigned additional digits for producer/supplier demonstration tempers and purchaser/user processed tempers.....	10
7.6.1	Temper designations for producer/supplier — Laboratory demonstration of response to heat treatment.....	10
7.6.2	Temper designations for producer/supplier — Demonstration of response to temper conversion.....	10
7.6.3	Temper designations for purchaser/user heat treatment.....	11
	Annex A (informative) Common, regionally applied temper designations and descriptions	12