ISO 2107:2007-02 (E)

Aluminium and aluminium alloys - Wrought products - Temper designations

Contents

Page

Foreword iv

1 Scope 1

2 Terms and definitions 1

3 Basis of codification 2

4 Basic temper designations 2
4.1 F -- as fabricated 2
4.2 O -- annealed 2
4.3 H -- strain-hardened 2
4.4 W -- solution heat-treated 2
4.5 T -- thermally treated to produce stable tempers other than F, O or H 3

5 Subdivisions of O temper designations 3
5.1 O1 -- high-temperature annealed and slow cooled 3
5.2 O2 -- thermo-mechanically processed 3
5.3 O3 -- homogenized 3

6 Subdivisions of H temper designations 3
6.1 General 3
6.2 First digit after H 3
6.3 Second digit after H 4
6.4 Third digit after H 5
6.5 Other digits after H 5

7 Subdivisions of T temper designations 5
7.1 First digits (numerals 1 to 10) after T 5
7.2 Additional digits added to designations T1 to T10 7
7.3 Assigned additional digits for stress-relieved T tempers 7
7.4 Assigned additional digits for stress-relieved W tempers 8
7.5 Assigned additional digits for variations of T7 type tempers 8

Annex A (informative) Demonstration of response to heat treatment 9