

DIN EN 15049:2007-12 (E)

Railway applications - Suspension components - Torsion bar, steel

Contents		Page
Foreword		5
Introduction		6
1	Scope	6
2	Normative references	6
3	Terms and definitions	7
4	Symbols and abbreviations	8
5	Requirements	9
5.1	Introduction	9
5.2	Documents to be provided by the customer	9
5.3	Documents to be provided by the supplier	10
5.4	Design analysis	10
5.5	Arrangement and design	10
5.6	Straight torsion bar ends and connections	12
5.6.1	General	12
5.6.2	Design of the straight torsion bar end	12
6	Product definition	13
6.1	Geometrical characteristics and space envelope	13
6.2	Mechanical requirements	13
6.2.1	Loading and allowable stresses	13
6.2.2	Service life	13
6.2.3	Investigation of the strain	13
6.2.4	Evaluation of the strain	14
6.3	Physical requirements	14
6.3.1	Material grade	14
6.3.2	Internal integrity	14
6.3.3	Inclusion cleanliness	14
6.3.4	Forged torsion bar ends	14
6.3.5	Decarburization	15
6.3.6	Surface condition	15
6.3.7	Residual compressive stresses on the surface	15
6.3.8	Grain size	16
6.4	Surface protection	16
6.4.1	Generalities	16
6.4.2	Temporary protection	16
6.4.3	Permanent protection	16
6.5	Characteristic moment of torsion / angular displacement	17
6.6	Mass	18
7	Mechanical properties for manufacturing	18
7.1	Hardness	18
7.2	Tensile strength	18
7.3	Toughness	18
8	Tests and test procedures	19
8.1	General requirements	19

8.2	Measuring equipment	19
8.3	Tensile strength	19
8.4	Toughness	19
8.5	Hardness	19
8.6	Material	19
8.7	Depth of decarburization	20
8.8	Grain size	20
8.9	Forged torsion bar ends	20
8.10	Residual compressive stresses on the surface	20
8.11	Surface defects	20
8.12	Surface condition	20
8.13	Dimensional check	21
8.14	Characteristic moment of torsion / angular displacement	21
8.15	Mass	21
8.16	Internal integrity	21
8.17	Surface protection	21
8.18	Loading and allowable stresses	21
9	Quality assurance and final approval	22
9.1	Quality assurance system and staff qualification	22
9.2	Product qualification procedures and samples	22
9.3	Control and monitoring of production quality	23
9.3.1	General	23
9.3.2	Quality assurance plan	23
9.3.3	Control by sampling lots	23
9.4	Requirements for control and monitoring of production quality	24
9.4.1	General	24
9.4.2	Non-compliance	26
9.4.3	Documentation	26
9.5	Handling instructions	26
10	Marking of torsion bars	26
11	Packaging	27
Annex A (normative) Material for hot formed and quenched and tempered torsion bars		28
A.1	General	28
A.2	Material for torsion bars, steel	28
Annex B (normative) Inspection of torsion bars made of round bars by the magnetic crack detection method		30
B.1	Object	30
B.2	Tests	30
B.3	Safety measures	30
Annex C (normative) Checking shot peening efficiency by ALMEN method		31
C.1	Field of application	31
C.2	Checking the procedure	31
C.3	Equipment and installations	31
C.3.1	ALMEN A2 test piece	31
C.3.2	Test piece holder	32
C.3.3	ALMEN measuring device	33
Annex D (normative) Examination for inclusions		34
D.1	Object	34
D.2	Test methods	34
D.2.1	Test method according to DIN 50602	34
D.2.2	Test method according to NF A 04-106	35

D.2.3	Test method according to SS 111116	35
Annex E (normative)	Taking of test pieces - Areas of the location of test pieces	36
Bibliography	38
Figures	Figure 1 -- Example for a straight torsion bar with mounted levers	11
	Figure 2 -- Example for a bended torsion bar	11
	Figure 3 -- Cylindrical or conical tooth system	12
	Figure 4 -- Frictional shrink fit	12
	Figure 5 -- Example of the distribution of stresses produced by shot peening as a function of depth	16
	Figure 6 -- Torsion bar diagram	17
Figure C.1	-- ALMEN test arrangements	32
Figure C.2	-- ALMEN measuring sytem	33
Figure E.1	-- Area "e" with constant diameter of the torsion bar to take test pieces	36
Figure E.2	-- Location of the test pieces for the tensile strength test	36
Figure E.3	-- Location of the test pieces for the notch impact test	37
Tables	Table 1 -- Symbols and definitions	8
	Table 2 -- Elements to be defined in the technical specification and agreed by the parties	10
	Table 3 -- Checks and tests to be carried out	24
	Table 4 -- Test pieces for statistical tests, number of tests	25
Table A.1	-- Guidance values for the maximum mechanical properties of quenched and tempered test pieces	29
Table D.1	-- Degree of cleanliness under the microscope according to DIN 50602 (procedure K), valid for non metallic oxide inclusions	34
Table D.2	-- Acceptable number of fields (small series and wide series) of each type	35
Table D.3	-- Degree of cleanliness by microscopic examination according to SS 111116 (maximum values)	35