

DIN EN 12680-1:2026-03 (E)

Founding - Ultrasonic testing - Part 1: Steel castings for general purposes

Contents		Page
European foreword		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Requirements	5
4.1	Order information	5
4.2	Extent of testing	6
4.3	Wall section zones	6
4.4	Maximum acceptable size of discontinuities	6
4.4.1	Acceptance limits for planar discontinuities mainly orientated perpendicular to the surface	6
4.4.2	Acceptance limits for volumetric discontinuities	6
4.4.3	Maximum acceptable discontinuities when radiographic testing (RT) of the casting is carried out as a supplement to ultrasonic testing (UT)	7
4.5	Qualification of personnel	7
4.6	Severity levels	7
5	Testing	7
5.1	Principles	7
5.2	Material	7
5.3	Equipment and coupling medium	8
5.3.1	Ultrasonic instrument	8
5.3.2	Probes	8
5.3.3	Checking of the ultrasonic test equipment	8
5.3.4	Coupling medium	8
5.4	Preparation of casting surfaces for testing	9
5.5	Test procedure	9
5.5.1	General	9
5.5.2	Range setting	9
5.5.3	Sensitivity setting	10
5.5.4	Consideration of various types of indications	10
5.5.5	Recording limits	11
5.5.6	Evaluation of discontinuities to be recorded	11
5.5.7	Characterization and sizing of discontinuities	11
5.6	Test report	12
Annex A (informative) Sound-beam diameters		20
Annex B (informative) Types of indications generated by typical discontinuities		22
Annex C (informative) Significant technical changes between this document and the previous edition		34
Bibliography		35