

# DIN EN ISO 19403-3:2024-11 (E)

## Paints and varnishes - Wettability - Part 3: Determination of the surface tension of liquids using the pendant drop method (ISO 19403-3:2024)

---

<b>Contents</b>		<b>Page</b>
<b>European foreword</b> .....		<b>3</b>
<b>Foreword</b> .....		<b>4</b>
<b>1</b>	<b>Scope</b> .....	<b>5</b>
<b>2</b>	<b>Normative references</b> .....	<b>5</b>
<b>3</b>	<b>Terms and definitions</b> .....	<b>5</b>
<b>4</b>	<b>Principle</b> .....	<b>5</b>
<b>5</b>	<b>Apparatus and materials</b> .....	<b>6</b>
<b>6</b>	<b>Sampling</b> .....	<b>7</b>
<b>7</b>	<b>Procedure</b> .....	<b>7</b>
	7.1 General.....	<b>7</b>
	7.1.1 Setting up the drop contour analysis device.....	<b>7</b>
	7.1.2 Test conditions.....	<b>8</b>
	7.2 Determination of the surface tension of the liquid.....	<b>8</b>
	7.2.1 Preparations.....	<b>8</b>
	7.2.2 Procedure.....	<b>8</b>
<b>8</b>	<b>Evaluation</b> .....	<b>8</b>
<b>9</b>	<b>Precision</b> .....	<b>9</b>
	9.1 General.....	<b>9</b>
	9.2 Repeatability limit, <i>r</i> .....	<b>9</b>
	9.3 Reproducibility limit, <i>R</i> .....	<b>9</b>
<b>10</b>	<b>Test report</b> .....	<b>9</b>
<b>Annex A (informative) Density of test liquids</b> .....		<b>10</b>
<b>Annex B (normative) Shape parameter, <i>B</i>, and Worthington number</b> .....		<b>11</b>
<b>Annex C (informative) Details of an interlaboratory test</b> .....		<b>12</b>
<b>Bibliography</b> .....		<b>15</b>