

DIN EN 13279-2:2014-03 (E)

Gypsum binders and gypsum plasters - Part 2: Test methods

Contents		Page
Foreword		3
Introduction		4
1	Scope	5
2	Normative references	5
3	Test conditions and sampling	5
3.1	Test atmosphere (reference test)	5
3.2	Sampling	5
3.3	Preparation of the sample	5
3.4	Water	5
3.5	Appliances and apparatus	6
4	Test methods for gypsum binders and gypsum plasters (including special purposes)	6
4.1	Sieve analysis (Fineness)	6
4.1.1	Apparatus	6
4.1.2	Determination of particles retained on 5 000 µm sieves	6
4.1.3	Determination of particles retained on 200 µm and 100 µm sieves	7
4.2	Determination of sulphur trioxide content and calculation of equivalent calcium sulfate	7
4.2.1	Principle	7
4.2.2	Apparatus	7
4.2.3	Reagents	8
4.2.4	Procedure	8
4.2.5	Expression of results	8
4.3	Determination of the water/plaster ratio	8
4.3.1	Sprinkling method	8
4.3.2	Dispersion method	9
4.3.3	Flow table method	10
4.4	Determination of the setting time	12
4.4.1	Knife method	12
4.4.2	Vicat cone method	13
4.5	Determination of mechanical properties	14
4.5.1	Apparatus	14
4.5.2	Preparation of the test specimen	17
4.5.3	Determination of hardness	17
4.5.4	Determination of flexural strength	18
4.5.5	Determination of compressive strength	18
4.6	Determination of adhesion	19
4.6.1	Principle	19
4.6.2	Apparatus	19
4.6.3	Procedure	19
4.6.4	Expression of results	20
Annex A (informative)	Water retention	22
Bibliography		23