

DIN EN 12150-1:2015-12 (E)

Glass in building - Thermally toughened soda lime silicate safety glass - Part 1: Definition and description

Contents	Page
European foreword	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Glass products	8
5 Fracture characteristics	8
6 Dimensions and tolerances	9
6.1 Nominal thickness and thickness tolerances	9
6.2 Width and length (sizes)	9
6.2.1 General	9
6.2.2 Maximum and minimum sizes	10
6.2.3 Tolerances and squareness	10
6.2.4 Edge deformation produced by the vertical process	11
6.3 Flatness	11
6.3.1 General	11
6.3.2 Measurement of overall bow	13
6.3.3 Measurement of wave and roller wave	14
6.3.4 Measurement of edge lift (for horizontally toughened glass only)	15
6.3.5 Measurement of perimeter deformation of glass produced by air cushion toughening process	16
6.3.6 Measurement of local distortion (for vertically toughened glass only)	17
6.3.7 Limitation on overall bow, roller waves and edge lift for horizontally toughened glass	17
6.3.8 Limitation on overall bow, wave and perimeter deformation for toughened glass manufactured by air cushion process	18
6.3.9 Limitation on overall bow and local distortion for vertically toughened glass	19
6.3.10 Other distortions	19
7 Edge and/or surface work, holes, notches and cut-outs	20
7.1 Warning	20
7.2 Edge working of glass for toughening	20
7.3 Profiled edges	21
7.4 Round holes	21
7.4.1 General	21
7.4.2 Diameter of holes	21
7.4.3 Limitations on position of holes	21
7.4.4 Tolerances on hole diameters	22
7.4.5 Tolerances on position of holes	23
7.5 Holes/others	23
7.6 Notches and cut-outs	24
7.7 Shaped panes	24
8 Fragmentation test	24

EN 12150-1:2015 (E) 8.1 General	24
8.2 Dimensions and number of test specimens	24
8.3 Test procedure	24
8.4 Assessment of fragmentation	25
8.5 Minimum values from the particle count	26
8.6 Selection of the longest particle	27
8.7 Maximum length of longest particle	27
9 Other physical characteristics	27
9.1 Optical distortion	27
9.1.1 Thermally toughened soda lime silicate safety glass produced by vertical toughening	27
9.1.2 Thermally toughened soda lime silicate safety glass produced by horizontal toughening	27
9.2 Anisotropy (iridescence)	27
9.3 Thermal durability	27
9.4 Mechanical strength	28
9.5 Classification of performance under accidental human impact	28
10 Marking	28
Annex A (informative) Curved thermally toughened soda lime silicate safety glass	30
Annex B (informative) Alternative method for the measurement of roller wave distortion	31
B.1 Apparatus	31
B.2 Method	31
B.3 Limitations	32
B.4 Alternative use of apparatus	32
Annex C (informative) Examples of particle count	33
Annex D (informative) Risk of spontaneous breakage of toughened glass due to nickel sulfide inclusion	36
Bibliography	37