

DIN EN 13108-7:2016-12 (E)

Bituminous mixtures - Material specifications - Part 7: Porous Asphalt

Contents		Page
European foreword		4
Introduction		6
1	Scope	7
2	Normative references	7
3	Terms and definitions, symbols and abbreviations	8
3.1	Terms and definitions	8
3.2	Symbols and abbreviations	10
4	Requirements for constituent materials	10
4.1	General	10
4.2	Binder	10
4.2.1	General	10
4.2.2	Selection of binder	11
4.3	Aggregates	12
4.3.1	Coarse aggregate	12
4.3.2	Fine aggregate	12
4.3.3	All-in aggregates	12
4.3.4	Added filler	12
4.4	Reclaimed asphalt	12
4.5	Additives	12
5	Requirements for the mixture	13
5.1	General	13
5.2	Composition, grading, binder content	13
5.2.1	Composition	13
5.2.2	Grading	13
5.2.3	Minimum binder content	15
5.3	Properties	16
5.3.1	Specimens	16
5.3.2	Drainage capacity	16
5.3.3	Resistance to permanent deformation	18
5.3.4	Water sensitivity	22
5.3.5	Particle loss	23
5.3.6	Low temperature properties	24
5.3.7	Friction after polishing	25
5.3.8	Coating and homogeneity	25
5.3.9	Reaction to fire	25
5.3.10	Binder drainage	25
5.3.11	Resistance to fuel for application on airfields	26
5.3.12	Resistance to de-icing fluid for application on airfields	27
5.3.13	Bitumen aggregate affinity for application on airfields	27
5.4	Temperature of the mixture	28
5.5	Regulated dangerous substances	28
5.6	Conflicting requirements	29
6	Assessment and verification of constancy of performance -- AVCP	29
7	Identification	29

Annex A (normative) Calculations of the penetration or the softening point of the binder of a mixture when reclaimed asphalt is used	31
A.1 General	31
A.2 Calculation of the penetration of the binder of a mixture	31
A.3 Calculation of the softening point of the binder of a mixture	31
Annex ZA (informative) Relationship of this European Standard with Regulation (EU) No. 305/2011	33
ZA.1 Scope and relevant characteristics	33
ZA.2 System of Assessment and Verification of Constancy of Performance (AVCP)	35
ZA.3 Assignment of AVCP tasks	35