

DIN EN 14488-3:2024-01 (E)

Testing sprayed concrete - Part 3: Flexural strengths (first peak, ultimate and residual) of fibre reinforced beam specimens

Contents		Page
European foreword		3
Introduction		4
1	Scope	5
2	Normative references	5
3	Terms and definitions	5
4	Symbols and abbreviated terms	6
4.1	Symbols	6
4.2	Abbreviations	7
5	Principle	7
6	Method A: Four point bending test on beam	7
6.1	Apparatus	7
6.1.1	Testing machine	7
6.1.2	Force application	8
6.1.3	Deflection measurement and control	9
6.2	Test specimen	9
6.2.1	General	9
6.2.2	Adjustment of test specimens	10
6.3	Procedures	10
6.3.1	Preparation and positioning of specimens	10
6.3.2	Loading	11
6.4	Expression of results	11
6.4.1	First peak and ultimate flexural strengths	11
6.4.2	Residual flexural strengths	12
6.5	Test report	13
6.6	Accuracy	13
7	Method B: Three point bending test on square panel with notch	14
7.1	Apparatus	14
7.1.1	Testing machine	14
7.2	Test specimens	15
7.2.1	Shape and size of test specimens	15
7.2.2	Manufacture and curing of test specimens	15
7.2.3	Notching of test specimens	15
7.3	Testing procedure	16
7.3.1	Preparation and positioning of test specimens	16
7.3.2	Bending test	19
7.4	Expression of results	19
7.4.1	Equivalence between CMOD and deflection	19
7.4.2	Limit of proportionality	20
7.4.3	Residual flexural tensile strength	20
7.5	Test report	22
7.6	Precision	22