

DIN 18515-1:2023-06 (E)

Cladding for external walls - Principles of design and application - Part 1: Tiles fixed with mortar

Contents

Page

Foreword	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Materials	8
4.1 General	8
4.2 Ceramic tiles	8
4.3 Split tiles and clinker bricks	8
4.4 Natural stone products	9
4.5 Cast stone	9
4.6 Factory-made mortar	9
4.7 Hydraulic thin-bed mortar	10
4.8 Reaction resin adhesives	10
4.9 Hydraulic grouts	10
4.10 Joint sealants	10
5 Requirements on external walls and fixing surfaces	10
5.1 Requirements on external walls	10
5.2 Requirements on fixing surfaces	10
5.2.1 General	10
5.2.2 Special requirements	11
5.3 Checking the fixing surfaces	12
6 Mortar selection	12
6.1 General	12
6.2 Selection of laying mortar as a function of the cladding material	12
6.3 Placing tiles	12
6.3.1 General	12
6.3.2 Building site conditions and influences of weather	13
6.3.3 Mixing the cementitious mortar	13
6.3.4 Mixing the reaction resin adhesive	13
6.3.5 Application of the laying mortar or adhesive on both sides (floating-buttering method), placing or laying of the covering and cladding materials	13
6.3.6 Wetting surface	13
6.3.7 Placing the cladding materials	14
6.4 Joints	14
6.4.1 Mortar joints	14
6.4.2 Movement joints	14
6.5 Built-in components	15
7 Production of fixing surfaces for tiles on anchored metal lath	15
7.1 General	15
7.2 Plaster with structural steel mesh reinforcement	15
7.3 Plaster applied on metal lath	15
7.4 Thermal insulation	16
8 Maintenance	16
Annex A (informative) Determination of the vapour diffusion resistance of the external wall cladding, taking into account the joint ratio	17
Annex B (informative) Determining the joint ratio as a function of joint width and cladding dimensions	18
Bibliography	20

Figures

Figure A.1 — Determining the vapour diffusion resistance of the external wall cladding, taking into account the joint ratio [1]..... 17

Tables

Table B.1 — Joint ratios in percent for a joint width of 10 mm..... 18
Table B.2 — Joint ratios in percent for a joint width of 8 mm 18
Table B.3 — Joint ratios in percent for a joint width of 5 mm 19
Table B.4 — Joint ratios in percent for a joint width of 3 mm 19