DIN EN 680:2006-03 (E)

Determination of the drying shrinkage of autoclaved aerated concrete

Contents

Page

Foreword 3

1 Scope 4

2 Normative references 4

3 Principle 4

4 Apparatus 4

5 Test specimens 5
5.1 Sample 5
5.2 Shape and size of the test specimens 5
5.3 Number of test specimens 5
5.4 Preparation of test specimens 6
5.5 Measurement of dimensions of test specimens and determination of their volume 6
5.6 Conditioning of test specimens 7

6 Testing procedure 7
6.1 Drying storage in a climate at (20 ± 2) °C and (45 ± 5) % relative humidity and determination of length changes and variations of mass 7
6.2 Drying of test specimens at (105 ± 5) °C 7

7 Test results 8
7.1 Calculation of relative length change 8
7.2 Calculation of moisture content 8
7.3 Determination of the conventional reference value of drying shrinkage 8
7.4 Determination of the total value of drying shrinkage 9
7.5 Calculation of the dry density 9

8 Test report 9